

Whitepaper

Type		
Features		
GSM	g/m ²	75±5
Whiteness	%	95-97
Color	—	L≤89 a 2.7-2.9, b -15,5±03
CIE	—	147-150
Thickness	um	100±1
Grey	%	25-26
Absorbtion	g/m ²	
Error of Thickness	%	≤5
Opaqueness	%	95-99
Folding Endurance	times	8-11
Moisture	%	5.0-5.5
Shrinking Rate	%	2.0-2.5
Strenght	mN.m	0.35-0.45/0.13-0.20
Smooth	s	18-23
Dust	spot/m2	≤0.5 mm ² ≤150; 0.5-1.5 mm ² ≤4; over 1.5 mm ² (None)